

ArtiPress G Gloss

TYPICAL END USES



Magazines



Brochures



Catalogues

COLOUR PROFILE

☑ ECI_PSR_LWC_ PLUS_V2.txt

FINISH

☑ Gloss

PRINTING METHODS

☑ Rotogravure

TECHNICAL DATASHEET (TARGET VALUES)

Substance		g/m2	65	70	75*	80*	90*
Brightness	D65/10°	%	89	90	91	91	91
Whiteness	CIE, ISO 11476, C2°	%	92	92	92	92	93
L*	D65/10°		93	93	93	93	93
a*	D65/10°		0.2	0.2	1.0	1.0	1.0
b*	D65/10°		-5.3	-5.3	-5.6	-5.6	-5.6
Opacity	D65/10°	%	93	94	94.5	95	96
Gloss Hunter	ISO 8254-1	%	64	66	66	66	66
Thickness	ISO 534	µm	53	55	60	63	72
Bulk	ISO 534	cm3/g	0.8	0.8	0.8	0.8	0.8
Smoothness	ISO 8791-4 PPS 1MPa	µm	0.7	0.7	0.7	0.7	0.7

Technical specifications are target values and may be subject to production variations.

*on request only



ENVIRONMENT

Renewable fibre
Recyclable paper
Recyclable packaging materials
Sustainable sources



REEL SPECIFICATIONS

Cores: 76 mm, 150 mm
Trimmed width: 7200 mm
Width: min. 388 mm, max. 4320 mm
Diameters: min. 1000 mm, max 1300 mm
Max. Weight: 10000 kg



CERTIFICATES

EU Ecolabel
ISO 9001
ISO 14001
ISO 50001
ISO 45001
FSC® CoC
PEFC™ CoC

STORAGE AND HANDLING

- Store the paper in a humidity and temperature controlled area at 50% relative humidity and room temperature between 19°C and 23°C.
- If the paper is stored in a non - air conditioned warehouse, it is absolutely necessary to allow a stabilization period in the print room.
- Open the protective wrapping at the moment of use.



Kabel Premium Pulp & Paper GmbH

Schwerter Straße 263
58099 Hagen
Tel +49 (0) 2331 699-0
sales@kabelpaper.de

