

NeoPress G Gloss

TYPICAL END USES



Catalogues



Magazines



Brochures



Leaflets

COLOUR PROFILE

☑ ECI_PSR_LWC_
STD_V2.txt

FINISH

☑ Gloss

PRINTING METHODS

☑ Rotogravure

TECHNICAL DATASHEET (TARGET VALUES)

Substance		g/m ²	42*	45	48	51	54	57	60
Brightness	D65/10°	%	71	71	71	74	74	74	75
Whiteness	CIE, ISO 11476, C2°	%	55	55	55	65	65	65	66
L*	D65/10°		89.5	89.5	89.5	90	90	90	90
a*	D65/10°		-1.1	-1.1	-1.1	-0,7	-0,7	-0,7	-0,7
b*	D65/10°		4.5	4.5	4.5	2.5	2.5	2.5	2.5
Opacity	D65/10°	%	85	87	89	90	91	92	93
Gloss Hunter	ISO 8254-1	%	50	51	52	53	55	57	57
Thickness	ISO 534	µm	38	40	42	44	45	48	49
Bulk	ISO 534	cm ³ /g	0.90	0.89	0.88	0.86	0.83	0.84	0.82
Smoothness	ISO 8791-4 PPS 1MPa	µm	0.8	0.8	0.7	0.7	0.7	0.7	0.7

Technical specifications are target values and may be subject to production variations.

*on request only



ENVIRONMENT

Renewable fibre
Recyclable paper
Recyclable packaging materials
Sustainable sources



REEL SPECIFICATIONS

Cores: 76 mm, 150 mm
Trimmed width: 7200 mm
Width: min. 388 mm, max. 4320 mm
Diameters: min. 1000 mm, max 1300 mm
Max. Weight: 10000 kg



CERTIFICATES

EU Ecolabel
ISO 9001
ISO 14001
ISO 50001
ISO 45001
FSC® CoC
PEFC™ CoC

STORAGE AND HANDLING

- Store the paper in a humidity and temperature controlled area at 50% relative humidity and room temperature between 19°C and 23°C.
- If the paper is stored in a non - air conditioned warehouse, it is absolutely necessary to allow a stabilization period in the print room.
- Open the protective wrapping at the moment of use.



Kabel Premium Pulp & Paper GmbH

Schwerter Straße 263
58099 Hagen
Tel +49 (0) 2331 699-0
sales@kabelpaper.de

